

Specification Sheet / 01 Betaflex 69



ISO9001, ISO14001, ISO45001
Certificate Ref: 11738

Description

Cellulose fibre type with nitrile rubber binder, which has low adhesion and corrosion in contact with aluminium alloys, iron and steel. This general purpose material is also resistant to oils, fuels and anti-freeze

Property	Measure	Value
Max. Temperature		150C
Medium density		Medium Fluid Absorbency
Medium swelling		Medium Compressibility
Thickness		0.4mm
Density		1.0 g/cm ³
Tensile Strength (across grain) N/mm ²		20.7
Compressibility	ASTM 7N/MM ²	14
Recovery		55%

ASTM Oil No3

22 hours at room temperature

Weight Increase	25%
Thickness Increase	4%

ASTM Fuel B

Weight Increase	28%
Thickness Increase	8%

Water

Weight Increase	30%
Thickness Increase	28%

The above figures are average values.

We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

