

Specification Sheet / 01 A355/C2004 Neoprene bonded cork



ISO9001, ISO14001, ISO45001
Certificate Ref: 11739

General Information and application

This is an economical and highly compressible material suitable for low and medium bolt pressure, with good flexibility and resilience.
The physical characteristics along with fuel and oil resistance make this a general purpose gasket material.

Material Description

Cork granule size 1-2mm
Colour- Black
Binder-Synthetic rubber

Physical Characteristics

Density-0.56-0.70
Hardness Shore A-55-75
Recovery after (%) - 30-50
Tensile Strength->80kg/cm
Transversal Direction >8
Longitudinal Direction >12

Flexibility

Original F=5-No cracks

Volume change after Immersion

ASTM No 1 Oil 70 Hrs @ 100c (%) -5 to +10
ASTM No 3 Oil 70 Hrs @ 100c (%) +10 to + 40
ASTM Fuel A, 22 Hrs @ 23c (%) -2 to + 10

Specification according to

ASTM 104-93 F229000

Change Control Date

20/1/17

Change

Created



The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

