Polymer Works, Hope Street Dudley, West Midlands DY2 8RS

## t: 01384 252555 f: 01384 252373 e: technical@advancedseals.co.uk

# Specification Sheet / 01 **Electrically Conductive Silicone Rubber Sheeting**

### **Availability**

65°shore A, Black, stock in thicknesses of 0.5mm, 0.8mm, 1.0mm, 1.6mm and 3.2mm Supplied in continuous roll lengths Widths of 915mm (standard) Pressure sensitive adhesive backing Punched and Water jet gaskets Strips and seals Fabrications

#### Temperature Range

Minimum(-54°C;-65°F) Maximum(260°C;500°F)

#### Specification

Electrically conductive grade silicone sheeting is designed to be used in many different applications. It is a carbon black filled silicone material that will act as a low amperage conductor, and also provide protection against electrostatic discharge. This material is available in continuous rolls or sheets. It is resistant to extreme high and low temperatures, and is proven to be an excellent gasketing material. Black is the only colour available. Sheet thickness ranges from 0.40mm up to 25.4mm thick.

#### Environmental Resistance

Silicone rubber products have an excellent resistance to: Ozone Oxidation Ultraviolet light Corona discharge Cosmic radiation Ionising radiation Weathering in general

| Property                            | Unit        | Typical Value | Test Method |  |
|-------------------------------------|-------------|---------------|-------------|--|
| Specific Gravity                    | g/cc        | 1.17          | ASTM D297   |  |
| Durometer                           | Shore A ±5  | 65 ±5         | ASTM D2240  |  |
| Tensile Strength                    | PSI         | 775           | ASTM D412   |  |
| Elongation                          | %           | 325           | ASTM D412   |  |
| Compression Set (22 Hrs @<br>100°C) | %           | 15            | ASTM D395   |  |
| Tear Strength                       | PSI Die "B" | 70            | ASTM D624   |  |
| Durometer                           | ohms-cm     | 5             |             |  |
| Change Control Date                 |             | Change        |             |  |
| 19/06/2019                          |             | Created       | Created     |  |

19/06/2019



The above figures are average values.

We recommend that you examine any material you select to ensure its suitability for your application. Tolerance(s) applied in accordance with ASG specification No WI007 (https://bit.ly/3nKm6Hj) unless otherwise stated. Our standard terms and conditions of trading (https://bit.ly/3b3mThw) apply at all times.





# http://www.advancedseals.co.uk



