

Specification Sheet / 01 A314 Semi Open Cell EPDM



ISO9001, ISO14001, ISO45001
Certificate Ref: 11738

Properties	Average Value
Cellular structure	Semi Open
Colour	Black
Density	100 +_20 kg/m ³
Temperature Range	- 40°C / + 120°C
Tear Resistance KG/cm (kN/m)	0,080
Ultimate elongation ASTM D412	> 200%
Compression Strenght 25% KGcmq(kPa)	0.14
Shore hardness	20+/-5
Fire resistant	(FMVSS 302)
Method of vulcanisation	Sulphur

Change Control Date	Change
29/07/2013	Created



The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3MThw>) apply at all times.

