

# Specification Sheet (Superceded) / 01 A350 (K) polyether polyurethane foam



ISO9001, ISO14001, ISO45001  
Certificate Ref: 11738

## Description

A combustion modified, conventional polyether polyurethane foam

## Typical physical properties

Physical properties are measured using test methods described in the BS4443 series and BS EN ISO 845:1995.

Nominal piece density range	23.5 – 25.5 kg/m <sup>3</sup>
Nominal hardness range	110-150 N
Nominal tensile strength	70 kPa min.
Nominal elongation at break	120% min.

## Foam Classification (BS3379)

Foam type CMB	Combustion Modified Conventional Slabstock
Nominal Classification	A

## Flammability characteristics

Complies with the requirements of Schedule 1, Part 1, The Furniture and Furnishings (Fire) (Safety) Amended Regulations 1989.

Capable of meeting the following	Under Writers Laboratories - UL94 HF1 Classification
Capable of meeting the following	Automotive FMVSS 302 ( Self extinguishing )

## Change Control Date

29/07/2013

## Change

Created



The above figures are average values.

We recommend that you examine any material you select to ensure its suitability for your application.  
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.  
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

