

Specification Sheet (Superceded) / 01 A350 (K) polyether polyurethane foam



ISO9001, ISO14001, ISO45001
Certificate Ref: 11738

Description

A combustion modified, conventional polyether polyurethane foam

Typical physical properties

Physical properties are measured using test methods described in the BS4443 series and BS EN ISO 845:1995.

| | |
|-----------------------------|-------------------------------|
| Nominal piece density range | 23.5 – 25.5 kg/m ³ |
| Nominal hardness range | 110-150 N |
| Nominal tensile strength | 70 kPa min. |
| Nominal elongation at break | 120% min. |

Foam Classification (BS3379)

| | |
|------------------------|--|
| Foam type CMB | Combustion Modified Conventional Slabstock |
| Nominal Classification | A |

Flammability characteristics

Complies with the requirements of Schedule 1, Part 1, The Furniture and Furnishings (Fire) (Safety) Amended Regulations 1989.

| | |
|----------------------------------|--|
| Capable of meeting the following | Under Writers Laboratories - UL94 HF1 Classification |
| Capable of meeting the following | Automotive FMVSS 302 (Self extinguishing) |

Change Control Date

| | |
|------------|--------------------------|
| 29/07/2013 | Change Created |
|------------|--------------------------|



The above figures are average values.

We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

