

Polymer Works, Hope Street  
Dudley, West Midlands DY2 8RS

t: 01384 252555

f: 01384 252373

e: technical@advancedseals.co.uk



http://www.advancedseals.co.uk

## Specification Sheet / 01 A330 Black Open Cell Sponge



ISO9001, ISO14001, ISO45001  
Certificate Ref: 11738

| Property  | Test Method        | Value          |
|---|--------------------|----------------|
| ASTM Spec (D1056-85)  | ASTM 1056 R012 1A2 |                |
| Colour  | -                  | Black          |
| Polymer   | -                  | Natural Rubber |
| At 25%  | -                  | 5-10 PSI       |
| Tensile Elongation  | -                  | 280kpa 250%    |
| Compression set 50% Deflection @ 70°C                           | -                  | 15% Max        |
| Accelerated Ageing - % Change in Compression Deflection at 70°C | -                  | +/- 20%        |
| Temperature Range   | -                  | -40°C to +80°C |
| Density Average Kg/M*   | -                  | 380 +/- 10%    |

| Change Control Date | Change  |
|---------------------|---------|
| 30/07/2013          | Created |



The above figures are average values.  
We recommend that you examine any material you select to ensure its suitability for your application.  
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.  
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

