

Polymer Works, Hope Street  
Dudley, West Midlands DY2 8RS

t: 01384 252555

f: 01384 252373

e: technical@advancedseals.co.uk



<http://www.advancedseals.co.uk>

## Specification Sheet / 01 A330 Black Open Cell Sponge



ISO9001, ISO14001, ISO45001  
Certificate Ref: 11739

Property	Test Method	Value
ASTM Spec (D1056-85)	ASTM 1056 R012 1A2	
Colour	-	Black
Polymer	-	Natural Rubber
At 25%	-	5-10 PSI
Tensile Elongation	-	280kpa 250%
Compression set 50% Deflection @ 70°C	-	15% Max
Accelerated Ageing - % Change in Compression Deflection at 70°C	-	+/- 20%
Temperature Range	-	-40°C to +80°C
Density Average Kg/M*	-	380 +/- 10%

Change Control Date	Change
30/07/2013	Created



The above figures are average values.

We recommend that you examine any material you select to ensure its suitability for your application.  
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.  
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

