

Polymer Works, Hope Street  
Dudley, West Midlands DY2 8RS

t: 01384 252555

f: 01384 252373

e: technical@advancedseals.co.uk



<http://www.advancedseals.co.uk>

## Specification Sheet (Superceded) / 01 Closed Cell Expanded EPDM



ISO9001, ISO14001, ISO45001  
Certificate Ref: 11739

Test Method	Specification	Typical Value
Density	0.45g/cm <sup>3</sup> - 0.55 g/cm <sup>3</sup>	0.5g/cm <sup>3</sup>
Compression Set 22hrs @ R.T 50 % Deflection	25% maximum	21%
Weather Resistance	No Cracks	No Cracks
Compression Deflection 25% Deflection	7 PSI ±2	6 PSI
Heat Aging 7 days @70 °c deflection change	± 30 %	+ 15 %
Material	Closed Cell Expanded EPDM	ASTM D1056,RE42,B2,C1

Change Control Date	Change
23/09/2013	Created



The above figures are average values.  
We recommend that you examine any material you select to ensure its suitability for your application.  
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.  
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

