

**Specification Sheet / 01**  
**A303 70 Shore \*\*\*Wras approved\*\*\* EPDM**



ISO9001, ISO14001, ISO45001  
Certificate Ref: 11738

<b>Specifications</b>	<b>Values</b>	<b>Test Method</b>	<b>Unit</b>
Compression Set(22 Hours @ 70°C)	20 %	ASTM D412	
Elongation at break	200%	ASTM D412	
Highest Recommended working temperature	100°C	None	
Intermittent Working Temperature	110°C	None	g/cm3
Lowest Recommended Working Temperature	-15°C	None	Mpa
Portable Water Temperature Rating	23°C	None	%
Shore Hardness (Shore A)	70 ° Shore	ASTM D2240	°C
Specific Gravity	1.22g/cm3	ASTM D2240	°C
Tensile Strength	9 MPA	ASTM D412	°C
WRAS Approval Number	1911536	None	%

WRAS Approval for cold water only

<b>Change Control Date</b>	<b>Change</b>
14/02/2018	Created



The above figures are average values.  
We recommend that you examine any material you select to ensure its suitability for your application.  
Tolerance(s) applied in accordance with ASG specification No W1007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.  
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

