

Polymer Works, Hope Street
Dudley, West Midlands DY2 8RS

t: 01384 252555

f: 01384 252373

e: technical@advancedseals.co.uk



<http://www.advancedseals.co.uk>

Specification Sheet / 01

A355/C2007 24.P TEC 924 Bonded cork



Certificate No. 11738-EMS-001
ISO 9001:2015 ISO 14001:2015

Physical Characteristics	Result	Method
Density	24(pcf) Min	ASTM F 1315
Tensile Strength (PSI)	175	ASTM F 152
Compressibility @ 100 PSI	10-25%	ASTM F 36
Recovery	65 % Min	
Cork granule size	1-2 mm	
Binder	Polymeric	

Volume change	Result	Method
ASTM No 1 Oil 70 Hrs @ 100c	Resists	
ASTM No 3 Oil 70 Hrs @ 100c	Resists	ASTM F146
ASTM Fuel A, 22 Hrs @ 21-30 c	Resists	

Specification according to

ASTM P2216-A

ASTM F104 call out F219 000

MIL HHC 576B Type 11B Class 3

Change Control Date	Change
06/05/15	Created



The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

