

Polymer Works, Hope Street
Dudley, West Midlands DY2 8RS

t: 01384 252555

f: 01384 252373

e: technical@advancedseals.co.uk



<http://www.advancedseals.co.uk>

Specification Sheet (Superceded) / 01 A357 Open Cell Polyether 18kg



Certificate No. 11738-EMS-001
ISO 9001:2015 ISO 14001:2015

Characteristic	Specification	Test Method
Average net piece density	17.1 – 18.9 Kg/m ³	BS EN ISO 845 : 2009 (ISO 845 : 2006)
Nominal hardness	105 - 145 Newtons	BS EN ISO 2439:METHOD B 2001/ASTM D3574
Tensile strength	70 kPa (Min)	BS EN ISO 1798: 2008
Elongation @ break	150 % (Min)	BS EN ISO 1798: 2008
Compression set (dry)	10 % (Max)	BS EN ISO 1856: 2001

Change Control Date	Change
02/01/2018	Created



The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No W1007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

