Polymer Works, Hope Street Dudley, West Midlands DY2 8RS

t: 01384 252555 f: 01384 252373

e: technical@advancedseals.co.uk



http://www.advancedseals.co.uk

## Specification Sheet (Superceded) / 01 EPDM Sponge Cord 0.6



Test Method	Specification	Actual Values
Type of Polymer	EPDM	
Density	0.55-0.65g/cm3	0.59g/cm3
Weather resistance	No cracks	No cracks
Compression-set 50% / 22hr at Room Temp	25% maximum	18%
Compression deflection 25% deflection	11 +-2 PSI	10 PSI
Heat ageing 7 days @70c Deflection Change	+-30%	+15%
Tolerances to BS3734 class E3		

Change Contro	l Date	Change
27/6/2019		Created



The above figures are average values.

We recommend that you examine any material you select to ensure its suitability for your application.

Tolerance(s) applied in accordance with ASG specification No WI007 (https://bit.ly/3nKm6Hj) unless otherwise stated.

Our standard terms and conditions of trading (https://bit.ly/3b3mThw) apply at all times.

