Polymer Works, Hope Street Dudley, West Midlands DY2 8RS

t: 01384 252555 f: 01384 252373 e: technical@advancedseals.co.uk

Specification Sheet (Superceded) / 01 **Expanded Epdm Cord 0.6**

Average Density 160 KG/M³ ASTM Spec D1056-85 2C2A1 B2 C E1 Water Absorption 5% Max 85/100°C Heat resistance in °C Consistent/Intermittent **Elongation at Break** 80% Compression set 50%/22hr/23 °C/24hr 25% Max Resistance to cold 3 Resistance to air and UV rays 3 Resistance to dilute acids 3 Resistance to alkalis 3 Resistance to animal or vegetable oils 3 Resistance to solvents: aliphatic 2 Resistance to solvents: Aromatic 1 Resistance to solvents: Chlorinated 3 Resistance to solvents: Ketonic 1 Resistance to swelling in oil and petrol 3 Acoustic and sound insulation 2 Classification; 1- Nil to weak

Value

3- good 4- excellent

| Change Control Date | Change |
|---------------------|---------|
| 01/11/2013 | Created |



The above figures are average values.

We recommend that you examine any material you select to ensure its suitability for your application. Tolerance(s) applied in accordance with ASG specification No WI007 (https://bit.ly/3nKm6Hj) unless otherwise stated. Our standard terms and conditions of trading (https://bit.ly/3b3mThw) apply at all times.



ASG advanced seals+gaskets

http://www.advancedseals.co.uk

2- average

Property



