

Polymer Works, Hope Street
Dudley, West Midlands DY2 8RS

t: 01384 252555

f: 01384 252373

e: technical@advancedseals.co.uk



<http://www.advancedseals.co.uk>

Specification Sheet / 01

A355/C2007 Polyurethane resin bonded cork



Certificate No. 11738-EMS-001
ISO 9001:2015 ISO 14001:2015

Material Description

Cork granule size 1-4mm

Binder-Polyurethane resin

Physical Characteristics

Specific weight 230kg/m³
13lb cu/ft

Hardness Shore A-61

Recovery after (%) - 90

Tensile Strength- 15 kgs/m²

Acoustic performance ^LW=33db (test report nr C/01/5l/0191/1)

Compression 50%

Resistance to acids 30 mins @100c No disintegration

Resistance to boiling water 2 hrs @100c No disintegration

Flexibility

No cracks, breaks or separation

Change Control Date

21/4/2020

Change

Created



The above figures are average values.

We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No W1007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

