

## Specification Sheet / 01 KT83EE Double Sided Filmic Tape



Certificate No. 11738-EMS-001  
ISO 9001:2015 ISO 14001:2015

### Technical Data

Carrier Description		Carrier Grade	
Polyprop		12 Micron	
Release Liner Grade	Release Liner Colour	Release Liner Weight	
Glassine	Amber	80 GSM	
Adhesive Type	Adhesive Grade	Adhesive Thickness	
Acrylic	GP	70 Micron	
Peel adhesion to steel	Loop tack	Release from liner	Temperature Range
1200 N/m	1000 N/m	10 N/m	-20°C to 120°C
Shelf Life	12 months stored in ambient room temp. conditions		
Shelf Life (Solid Rubbers)	3-6 months		
Change Control Date	Change		
07/05/2014	Created		



The above figures are average values.  
We recommend that you examine any material you select to ensure its suitability for your application.  
Tolerance(s) applied in accordance with ASG specification No WI007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.  
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

