

Polymer Works, Hope Street
Dudley, West Midlands DY2 8RS

t: 01384 252555

f: 01384 252373

e: technical@advancedseals.co.uk



<http://www.advancedseals.co.uk>

Specification Sheet / 01

A316 (WHITE) White Closed Cell EPDM Sponge



Certificate No. 11738-EMS-001
ISO 9001:2015 ISO 14001:2015

Property	Result
Colour	White
Size - skin / skin	2000mm x 1000mm x 60mm (± 4mm)
Compression @ 25% Deflection (kPa) ASTM D1056	30-45 (35)
Compression Deflection @ 50% (kPa) ASTM D1056-00	95
Density (kg/M³) ISO 845-95	123 ± 20
Compression Set (50% 22h) ASTM D1056-00 @ 23°C	27% (<30%)
Heat Ageing, Change in Compression Deflection, 72hrs @ 70 °C	± 5% (<10%)
Elongation at Break (%) ISO 1798-7	150% (>100%)
Tensile Strength (kg/cm²) ISO 1798-7	4.5 (>4.5)
Resistance to Air and UV	Excellent
Resistance to Oil	Poor
Resistance to Acids	Good
Temperature Range (consistent)	-40 / +80 (degrees Celsius)
Temperature Range (intermittent)	-40 / +120 (degrees Celsius)
Sulphur Content	Sulphur Free

Change Control Date	Change
23/01/2020	Created
09/10/2023	Sulphur Free confirmation added



The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No W1007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

